



Technical datasheet

AGGLOMERATED CORK ROLLS

Ref. 15 MS



FTR 15MS/3 EN 2020

DESCRIPTION



- Natural, recyclable and from a renewable raw material product,
- Good thermal and acoustic insulation, reducing sound propagation, impact noise and energy consumption;
- High durability and dimensional stability even when subject to high temperature variations;
- Anti-static and anti-allergic;
- Resistant and flexible;
- Contrary to other synthetic products It does not free solvents nor dangerous compounds;
- Allows levelling of small defects of the floors;
- Appropriate for heated floors ($R < 0.15 \text{ m}^2 \cdot \text{K/W}$);
- Natural cork underlayment for commercial and residential applications;
- Available in different dimensions (Width from 500 to 1400 mm; Thickness from 1,2 to 12 mm)

TECHNICAL SPECIFICATIONS

Characteristic	Specification	Standard
Grain size	1-5 mm	ISO 2030
Tolerance on length and width	nominal value $\pm 1\%$	EN 426
Thickness	$\pm 0,2 \text{ mm}$	EN 428
Density	200-240 Kg/m^3	EN 672
Compression	20 – 40 %	ISO 7322
Tensile strength	$\geq 200 \text{ KPa}$	ISO 7322
Flexibility	Factor 5: Pass	EN 435/A

Resistance to boiling water	Absence of disintegration after 3 hours in boiling water	ISO 7322
Impact noise reduction	17 dB (indicative value for 2 and 4 mm thickness) 18 dB (indicative value for 5 and 6 mm thickness)	ISO 140-8
Sound absorption coefficient	$\alpha_w = 0.05$ (indicative value for 2 and 4 mm thickness)	EN ISO 11654
Fire Resistance	Class E - Cork is a fire inhibitor which neither spreads flame nor releases toxic gases on combustion	EN 13501-1
Thermal conductivity	0.049 W/m.K	ISO 8302
Thermal Resistance	2 mm - 0.04 m ² .K/W 4 mm - 0.08 m ² .K/W 6 mm - 0.12 m ² .K/W	ISO 8302
Formaldehyde	It was not added during manufacture formaldehyde	---

Note: technical specifications may be changed without previous notice.

Characteristic	Specification	Result	Class	Standard
Punctual Conformability (PC)	≥ 0.5 mm	≥ 1.2 mm	PC2	EN 16354
Compression Strength (CS)	≥ 60 kPa	≥ 200 kPa	CS3	EN 16354
Compression Creep (CC)	≥ 35 kPa	≥ 50 kPa	CC3	EN 16354
Dynamic Load (DL)	≥ 100.000 cycles	≥ 250.000 cycles	DL3	EN 16354

Testing according to MMFA/EPLF higher requirements group 1 and 2.

Note: technical specifications may be changed without previous notice



SECURITY DECLARATION

We ensure that the cork agglomerate rolls 15 MS are made with cork granules and that the glue used in the agglomeration is based on formaldehyde-free polyurethane. This product does not release any toxic components and does not represent a health hazard for those who handle it.